

Conbextra EP10

High Strength Epoxy Resin Grout

Uses

Provides a free flowing grout, for use where physical properties and chemical resistance of the hardened grout are of utmost importance. It is suitable for a wide range of heavy duty applications including;

- Underplate grouting to substantial structural elements.
- Base plate grouting in dynamic load situations such as turbines and other reciprocating machinery.
- Heavy industrial applications in steelworks, refineries chemical plants and electroplating works. Structural infill where very high strength is required.
- Rail track applications, to support heavy cranes, or on transporter rails.

Advantages

- Excellent durability - high compressive, flexural and tensile strengths ensure a long working life.
- Cost effective - high early strength gain promotes minimum downtime and early commissioning of plant.
- User friendly - simple, full pack mixing to ensure that the performance characteristics are achieved.
- Versatile - suitable for a wide range of loading situations including repetitive dynamic loads.
- Excellent in service performance - non-shrink capability ensures full surface to surface contact.

Description

Conbextra EP10 is a solvent free epoxy resin grout designed for grouting of gap widths of 0.25 – 10mm. It is an all liquid system consisting of base and hardener. The components are supplied in the correct mix proportions designed for whole pack mixing on site.

Technical Support

Fosroc offers a comprehensive range of high quality, high performance construction products. In addition, Fosroc offers a worldwide technical support and on-site service to specifiers, end-users and contractors.

Properties

Compressive strength	57 N/mm ² at 1 day
	66 N/mm ² at 3 days
	93 N/mm ² at 7 days
Flexural strength	63 N/mm ² at 7 days
Tensile strength	26 N/mm ² at 7 days
Density	Approximately 1050 kg/m ³
Pot life	90 min. at 20°C
	40 min. at 35°C

Specification Clauses

Where shown on the contract documents, the epoxy grout shall be Conbextra EP10 supplied by Fosroc. It shall provide good general chemical resistance, and a 7 day compressive strength of at least 93 N/mm².

Instructions for Use

Preparation

Underplate grouting

The unrestrained surface area of the grout must be kept to a minimum. Generally, the gap between the perimeter formwork and the plate edge should not exceed 75 mm on the pouring side and 25 mm on the opposite side. Formwork on the flank sides should be kept tight to the plate edge. Air pressure relief holes should be provided to allow venting of any isolated high spots.

Formwork

The formwork should be constructed to be leak proof as Conbextra EP10 is a free flow grout. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints. For free flow grout conditions, it is essential to provide a hydrostatic head of grout. To achieve this a feeding hopper should be used - please consult your local Fosroc office for more details.

Conbextra EP10

Foundation surface

This must be free from oil, grease, or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris.

Base plate

If delay is likely before placing steel base plates, it is recommended that the underside and edges are coated with Nitoprime 25* to prevent rust formation and ensure bonding with the Conbextra EP10 grout. All metal surfaces should be cleaned to a bright finish in accordance with Swedish Standard SA 2½ or equal. Nitoprime 25 can be applied directly onto newly cleaned steel surfaces even if they are damp.

Mixing

The entire contents of the hardener can should be poured into the base container and mixed for 2-3 minutes or until uniform colour is achieved. Once mixed, the material must be used within the specified pot life (see under Properties).

Note: Immediately prior to placement, all surfaces must be dry.

Placing

Ensure that the grout can be placed within its pot life. Continuous grout flow is essential. Sufficient grout must be available prior to starting and the time taken to pour a batch must be regulated to the time taken to prepare the next one. Pouring should be from one side of the void to eliminate air entrapment. The hydrostatic head must be maintained at all times so that a continuous grout front is achieved.

Cleaning

All tools and equipment should be cleaned immediately after use with Fosroc Solvent 102.

Limitations

Grouts should not be placed in any unrestrained situation, i.e. base plate plinths, etc. Failure to comply may lead to crack development in the grout.

Estimating

Supply

Conbextra EP10	:	1 litre pack
Nitoprime 25	:	1 & 4 litre pack
Fosroc Solvent 102	:	5 litre packs

Coverage

Nitoprime 25	:	4.0 to 5.0 m ² /litre
--------------	---	----------------------------------

Storage

When stored in warehouse conditions below 35°C, Conbextra EP10 will have a shelf life of 12 months

Precautions

Health and Safety

Some people are sensitive to epoxy resin so gloves and a barrier cream such as Kerodex 71, Rozalex 9, Debba Wet Work or similar should be used when handling these products. If contact with the resin occurs, it must be removed before it hardens with a resin removing cream such as Kerocleanse 22 or Rozalex 42. Follow by washing with soap and water. Do not should accidental eye contamination occur, wash thoroughly with plenty of clean water and seek medical treatment immediately.

Fire

Nitoprime 25 and Fosroc Solvent 102 are flammable.

Flash points

Nitoprime 25	:	39°C
Fosroc Solvent 102	:	33°C



Fosroc Sdn. Bhd.

No 8 Jalan Trompet, 33/8
Seksyen 33, 40400 Shah Alam
Selangor, Malaysia.

Branch Office:

29, Jalan Zainal Abidin,
10400 Penang, Malaysia.

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

telephone:
+60 3 5191 5660

fax:
+60 3 5191 6960

email:
enquiry@malaysia.fosroc.com

+60 4 2287 464

+60 4 2292661

