

# Dr. Fixit Pidifin 2K

## 2-PARTS FLEXIBLE CEMENTITIOUS WATERPROOFING MEMBRANE

### Description

**Dr. Fixit Pidifin 2K** is 2 parts polymer-modified flexible cementitious waterproofing membrane coating specially formulated for Concrete and Masonry Surface which is supplied in ready-mix kits (2 parts). When the dry part is mixed with acrylic-modified emulsion and applied according to direction, the cured.

**Dr. Fixit Pidifin 2K** will become a tough, flexible and seamless waterproof membrane and acts as an excellent water barrier to Concrete and Masonry Surface.

### Area of Application

- Concrete foundations, basements wall and lift pits.
- Swimming pools, water tanks and reservoirs
- Concealed roofs, parking decks, bathroom, toilet, kitchen, balconies and planters.
- Any other concrete, cement or masonry surface subject to damage from moisture.

### Features & Benefits

- Quick drying
- Easily applied by brush or trowel
- Flexible
- Excellent adhesion to concrete and masonry substrates
- Non toxic substances
- Environmentally friendly - free Volatile Organic Compound (VOC)
- Can be applied on damp surface.
- Excellent waterproofing property - No leakage up to 10 m. hydrostatic pressure.

### Method of Application

#### 1 Surface Preparation

- Allow new concrete and masonry substrate to fully cure prior application.
- All surfaces must be free from oil, grease, wax, dirt or any other form of foreign matter which might effect adhesion. Spalled Concrete must be sound before applied.
- Substrate should be reach a "Saturated Surface Dry" (SSD) condition (damp, without standing water)

#### 2 Mixing

- Using Portland mechanical mixer, slowly add Powder part to Liquid part in a clean container until a smooth and homogenous slurry mixture is achieved.
- Allow the mixed slurry to stand for 5-10 minutes for releasing air-trapped during the mixing prior to application. Mixing material must be use within recommend pot life.

#### 3 Applications

- **Dr. Fixit Pidifin 2K** slurry can be applied by brush or trowel. **DO NOT** dilute with water. Recommended coverage rate is approximately 1.1 kg./m<sup>2</sup>/coat for 0.8 mm. thick of wet film thick (minimum 2 coat.)
- Allow the slurry to cure for at least 1 hour before applying a second coat.

#### 4 Curing

- For maximum protection, allow 12 to 24 hours curing time after the second coat.
- Dr. Fixit Pidifin 2K requires at least 7 days before filling spas, swimming pools and water tanks with water as well as mock-up or ponding tests on site" to 'requires at least 7 days before filling spas, swimming pools and water tanks with water as well as mock-up or ponding tests on site'

# Dr. Fixit Pidifin 2K

2-PARTS FLEXIBLE CEMENTITIOUS  
WATERPROOFING MEMBRANE

## 5 Cleaning

- **Dr. Fixit Pidifin 2K** can be removed from tools and equipment immediately after use with clean water, only hardened material can be removed mechanically.

## Technical Information

Properties	Specification / Standard	Results
Mix Component	-	Mix Ratio 1 : 2 (A : B)
Polymer Content	-	> 18 %
Water Absorption	-	< 6%
Proprietary Polymer	-	High quality modified acrylic polymer
Set-to-touch time	ASTM D 1640	45 min
Tensile Strength - as cast	ASTM D 412	2.5 N/mm <sup>2</sup>
Elongation at Break - as cast	ASTM D 412	60 %
Adhesion to Substrate	ASTM D 4541	0.80 N/mm <sup>2</sup>
Adhesion to Concrete at 7 day	ASTM D 4541	1.75 N/mm <sup>2</sup>
Immersion in water Adhesion to Concrete at 7 day	ASTM D 4541	1.00 N/mm <sup>2</sup>
Crack Bridging	ASTM C 836	1 mm

## Precautions & Limitations

- **Dr. Fixit Pidifin 2K** is not suitable for traffic area application.
- **Dr. Fixit Pidifin 2K** is a pre measure package. Do not dilute with water or add any more sand or cement.

## Packaging

Product	Packaging	Coverage
Dr. Fixit Pidifin 2K	15 kg./set	1 kg./m <sup>2</sup> /coat (minimum 2 coat)

## Storage

- 12 month storage in sealed container and room temperature

## Health & Safety Precautions

- Non Flammable
- Avoid contact with skin and eyes. Any splashes to the skin or eyes should be washed off with clean water
- Wear mask when mixing.
- Wear protective gloves and eye protection when applied.



### Pidilite Bamco Limited

(A group company of Pidilite Industries Ltd.)  
699 Modernform Tower 15 FL., Srinakarin Rd.,  
Suan Luang, Bangkok 10250, THAILAND.  
T +662 722-8535 F +662 722-8381  
website [www.pidilitebamco.com](http://www.pidilitebamco.com)  
E-mail [sales@pidilitebamco.com](mailto:sales@pidilitebamco.com)

**DISCLAIMER** The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The Company does not assume any liability or any consequential damage for unsatisfactory results, arising from the use of our products.

**HOTLINE : (+662) 722-8535 # 101**