

Hydroproof Xtra

Single component acrylic polymer for cement based waterproof composite coating membrane

Uses

Provides an effective and economical method of waterproofing to concrete and masonry surfaces, by mixing with cement and application by brush.

Advantages

- Non - toxic, non-flammable and user friendly
- Provides a tough, impermeable waterproof membrane
- Can be applied by brush, on horizontal and vertical surfaces
- Excellent adhesion to concrete and masonry surfaces
- Protects concrete and mortar from natural elements such as wind, rain, sunlight
- Breathable - allows inside water vapour to escape

Description

Hydroproof Xtra is formulated to be mixed with cement on site or simply brush applied over concrete or masonry surfaces to provide an effective waterproof membrane.

Technical support

Fosroc provides a technical advisory service supported by a team of specialists in the field.

Areas of application

Below sloping screed or waterproof plaster on :

- Roofs, terraces and balconies as a sandwich layer
- Pools and fountains
- Reservoirs and channels
- End walls subjected to rain

Properties

Water absorption	: 1% maximum
Pot life at 30°C	: 30 min.
Application temperature	: Not less than 10°C
Toxicity	: Non-toxic
Bond strength to concrete	: Approx. 1 N/mm ²

Application instructions

Preparation

All surfaces to be treated with Hydroproof Xtra must be thoroughly cleaned by a wire brush or other mechanical means, to remove all dust, laitence or debris. The surface must also be free from oil, grease, wax or any other form of foreign matter which might affect adhesion. Spalled and deeply disintegrated concrete or mortar must be removed to a sound substrate and repaired suitably before coating.

Priming

Before application, the surface should be primed with Hydroproof Xtra as follows:

1 part of Hydroproof Xtra : 2 parts of Water : 4 parts of Cement

Mixed material with the above proportion will cover an area of 16-17m² for 1L of Hydroproof Xtra.

Topcoat

Hydroproof Xtra acrylic polymer shall be mixed with neat cement in the ratio of 1:2 respectively, to obtain a uniform and consistent slurry avoiding any lump formation. This can be achieved with a low duty, low speed drilling machine attached with a mixing paddle. Do not mix for more than 2 minutes. Do not mix more material than which can be used within the pot life. Retempering the mix with water should not be done. Occasionally stir the material till the entire quantity is applied, so that solids do not settle at the bottom of the container.

Mixing Ratio

Hydroproof Xtra liquid	Neat cement
0.5L	1 kg
1L	2kg
5L	10 kg
20L	40 kg

For white colour - mix white cement, for other colours, add cement compatible pigments to white cement.

Application

For best results, wet the surface before coating. Apply the mix with a short, stiff bristle brush like a paint to an approximate thickness of 1 to 2mm. During the first 12 hours of curing, Hydroproof Xtra surface must be protected from abrasion, rain or other adverse conditions. No traffic shall be allowed within 48 hours after application.

Normally 2 coats of application of Hydroproof Xtra are recommended. First coat should be allowed to air dry for 5 - 6 hours. After application of the final coat, initial air drying shall be allowed for 2 to 6 hours. During this period water should not be used for curing. Moist curing should be done for the next 24 hours by spraying water on Hydroproof Xtra coating. Following moist curing, Hydroproof Xtra should be allowed to dry for three days before subjecting it to submersion in water.

Hydroproof Xtra

Estimating

Packaging

Available in 0.5, 1, 5 & 20 L packs.

Coverage

Priming coat - 16-17m² / L.

Topcoat - 4.5 - 5.0m² / L / coat.

However the practical consumption varies depending on the texture and porosity of the surface and the application thickness.

Storage

Hydroproof Xtra liquid has a shelf life of 12 months, when stored in unopened containers under normal warehouse conditions.

Precautions

Health & Safety

Hydroproof Xtra is water based and non-toxic. Gloves should be worn during application. Any splashes on the skin or eyes must be washed off with clean water. In case of prolonged irritation medical advice should be sought.

Fire

Hydroproof Xtra is nonflammable.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 024

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-42521900

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

No. 26(old no.33), 1st Floor,
1st Street Postal Colony,
West Mambalam,
Chennai 600 033.
Ph: 044-24899949-94
Fax: 044-24896641

Mumbai

1401/1402, 14th Floor,
A-Wing 'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022-43406800-04
Fax: 022-27562423

Noida

D-166 Sector 10
Dist. Gautam Budha Nagar,
Noida,
UP 201 301
Ph:0120-4270620-21
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188
Fax: 033-2499-0280